

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
5 February 2004 (05.02.2004)

PCT

(10) International Publication Number
WO 2004/011547 A1

(51) International Patent Classification?: C08L 23/06,
23/04, B65D 1/00

SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number:
PCT/EP2003/007941

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(22) International Filing Date: 18 July 2003 (18.07.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02078183.7 25 July 2002 (25.07.2002) EP

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted
a patent (Rule 4.17(ii)) for the following designations AE,
AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH,
CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IN, IS, JP, KE, KG,
KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG,
MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU,
SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG,
UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,
GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR),
OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG)
— of inventorship (Rule 4.17(iv)) for US only

(71) Applicant (*for all designated States except US*): SOLVAY
POLYOLEFINS EUROPE-BELGIUM (S.A.) [BE/BE];
Rue du Prince Albert, 44, B-1050 Brussels (BE). —

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): GORGERIN, Michel,
Oswald [BE/BE]; Rue D'Ecaussinnes, 2, B-7062 Soignies
(BE).

(74) Agent: SMITH, Julian, Philip, Howard; BP Interna-
tional Limited, Patents and Agreements, Chertsey Road,
Sunbury on Thames, Middlesex TW16 7LN (GB).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: CONTAINER FORMED FROM MULTIMODAL ETHYLENE POLYMER

(57) **Abstract:** A container is disclosed comprising a multimodal ethylene polymer having a standard density of at least 950 kg/m³ and a fluidity index MI₂ of from 1 to 10 g/10 min, said multimodal ethylene polymer comprising: from 20 to 65 wt%, based on the total weight of the multimodal ethylene polymer, of a fraction comprising ethylene polymer (A) having a density of more than 965 kg/m³ and a fluidity index MI₂(A) of at least 10 g/10 min; and from 80 to 35 wt %, based on the total weight of the multimodal ethylene polymer, of a fraction comprising a copolymer (B) of ethylene and at least one alpha-olefin containing from 3 to 12 carbon atoms, and having a fluidity index MI₂(B) of less than 10 g/min and a content of said alpha-olefin(s) of 0.1 to 5 mol%.

BEST AVAILABLE COPY

WO 2004/011547 A1